



CERTIFICATE OF ANALYSIS

| | | | |
|----------------------------|------------------------------|------------------------------|------------------------|
| CUSTOMER NAME | BARSUKOV EVGENII MIHAILOVICH | DATE OF SAMPLING | 20/05/2022 |
| PRODUCT NAME | RUXX OIL GL 4/5 75W-90 | SAMPLE RECEIVED DATE | 22/05/2022 12:00:00 AM |
| | | NAME OF THE SAMPLER | Pardeep |
| PRODUCT DESCRIPTION | RUXX OIL GL 4/5 75W-90 | SAMPLE RECEIVED BY | Uzair |
| | | SAMPLE REVIEWING TIME | 12:00 AM |
| | | QUANTITY OF THE BLEND | 1200 |
| | | SAMPLING POINT | BLENDING SECTION K-1 |
| | | RESULT REPORTING DATE | 22/05/2022 |

The above sample (s) was/were examined as detailed below and following results obtained

| CHARACTERISTICS | ASTM METHOD | UNIT | RESULTS |
|----------------------------|-------------|------|---------|
| Appearance | Visual | | c&b |
| Density @ 15 °C | ASTM D-4052 | g/ml | 0.844 |
| Color* | ASTM D-1500 | | GREEN |
| Water* | Crackle | | NIL |
| Kinematic Viscosity @100°C | ASTM D-445 | cSt | 14,51 |
| Kinematic Viscosity @ 40°C | ASTM D-445 | cSt | 88,2 |
| Viscosity Index | ASTM D-2270 | | 172 |
| Flash Point , COC | ASTM D-92 | °C | 191 |
| Pour Point | ASTM D-97 | °C | -45 |

CHECKED BY: Sarra

APPROVED BY: Bipin

SAMPLE CONDITION: NORMAL

The Test Report shall not be reproduced (except full) without the written approval of United Grease & Lubricants

Sample retention period is 6 monts only, Unless otherwise instructed by United Grease & Lubricants in writing

Test parametrs included for filling are according to the requirements.

The report is generated electronically .signature is not required.

* Not Included in the scope of ISO 17025:2017 Accreditation

AN ISO 9001:2015, ISO 14001:2015, ISO 45001-2018 CERTIFIED COMPANY , Accredited testing ISO/IEC 17025 :2017 No. ATL 0047

P.O .Box :2685, Ajman-United Arab Emirates

Tel:00971-6-7436521, Fax:00971-6-7439709

E-mail:ugllube@eim.ae, Website:www.unitedgrease.com

QA: F/36; Revision:02; Date: 22/05/2022

| CHARACTERISTICS | ASTM METHOD | UNIT | RESULTS |
|--------------------------------|-------------|-------|---------|
| Foaming , [tendency/Stability] | ASTM D-892 | | |
| Seq I | | mL/mL | 10/0 |
| Seq II | | mL/mL | 10/0 |
| Seq III | | mL/mL | 10/0 |

CHECKED BY: Sarra

APPROVED BY: Bipin

**SAMPLE
CONDITION:**

NORMAL

The Test Report shall not be reproduced (except full) without the written approval of United Grease & Lubricants

Sample retention period is 6 months only, unless otherwise instructed by United Grease & Lubricants in writing

Test parameters included for filling are according to the requirements.

The report is generated electronically. Signature is not required.

* Not Included in the scope of ISO 17025:2017 Accreditation

AN ISO 9001:2015, ISO 14001:2015, ISO 45001:2018 CERTIFIED COMPANY, Accredited testing ISO/IEC 17025 :2017 No. ATL 0047

P.O. Box :2685, Ajman-United Arab Emirates

Tel:00971-6-7436521, Fax:00971-6-7439709

E-mail:ugllube@eim.ae, Website:www.unitedgrease.com

QA: F/36; Revision:02; Date: 22/05/2022

For **UNITED GREASE AND LUBRICANTS CO. L.L.C**

Authorised Signatory

