



### CERTIFICATE OF ANALYSIS

<b>CUSTOMER NAME</b>	BARSUKOV EVGENII MYKHAILOVICH	<b>DATE OF SAMPLING</b>	01/03/2022
<b>PRODUCT NAME</b>	RUXX Oil 5W/30 API SN/CF CITY LIFE Fully Synthetic	<b>SAMPLE RECEIVED DATE</b>	01/03/2022 00:00:00
<b>PRODUCT DESCRIPTION</b>	RUXX Oil 5W/30 API SN/CF CITY LIFE Fully Synthetic	<b>NAME OF THE SAMPLER</b>	Pardeep
<b>SAE/ISO</b>	5W/30	<b>SAMPLE RECEIVED BY</b>	Sariyan
<b>API</b>	SN/CF	<b>SAMPLE REVIEWING TIME</b>	12:00 AM
		<b>QUANTITY OF THE BLEND</b>	5950
<b>PACKAGE</b>	12X1L=50 6X4L=50 208l=20	<b>SAMPLING POINT</b>	BLENDING SECTION K-4
		<b>RESULT REPORTING DATE</b>	01/03/2022

The above samples were tested as detailed below and the following results were obtained.

CHARACTERISTICS	ASTM METHOD	UNIT	RESULTS
Appearance	Visual		C&B
Density at 15 °C	ASTM D-4052	g/ml	0.8481
Color*	ASTM D-1500		L3.0
Water*	Crackle		ZERO
Kinematic viscosity at 100°C	ASTM D-445	cSt	10.31
Kinematic viscosity at 40°C	ASTM D-445	cSt	55.95
Viscosity Index	ASTM D-2270		176
Total Base number	ASTM D-2896 - Procedure B	mgKOH/g	10.2
Flash point, COC	ASTM D-92	FROM	230
Pour Point	ASTM D-97	FROM	-45
Foaming, [tendency/Stability]	ASTM D-892		
Sequence I		ml/ml	0/0

**CHECKED BY:** Sara

**APPROVED BY:** Bipin

**SAMPLE CONDITION:**

NORMAL

The Test Report shall not be reproduced (except full) without the written approval of United Grease & Lubricants

Sample retention period is 6 months only, unless otherwise instructed by United Grease & Lubricants in writing

Test parameters included for filling are according to the requirements.

The report is generated electronically. Signature is not required.

\* Not Included the scope of ISO 17025:2017 Accreditation

AN ISO 9001:2015, ISO 14001:2015, ISO 45001:2018 CERTIFIED COMPANY, ISO/IEC 17025:2017 accredited testing No. ATL 0047

PO .Box :2685, Ajman-United Arab Emirates

Tel: 00971-6-7436521, Fax: 00971-6-7439709

Email: uglube@eim.ae , Website: www.unitedgrease.com

Quality Control: F/36; Revision:03; Date: 01/03/2022



## CERTIFICATE OF ANALYSIS

CHARACTERISTICS	ASTM METHOD	UNIT	RESULTS
Sequence II		ml/ml	0/0
Sequence III		ml/ml	0/0
Apparent viscosity according to CCS at -30°C	ASTM D-5293	mPa.s	6600

CHECKED BY: Sara

APPROVED BY: Bipin

SAMPLE  
CONDITION:

NORMAL

The Test Report shall not be reproduced (except full) without the written approval of United Grease & Lubricants

Sample retention period is 6 months only, unless otherwise instructed by United Grease & Lubricants in writing

Test parameters included for filling are according to the requirements.

The report is generated electronically. Signature is not required.

\* Not Included the scope of ISO 17025:2017 Accreditation

AN ISO 9001:2015, ISO 14001:2015, ISO 45001:2018 CERTIFIED COMPANY, ISO/IEC 17025:2017 accredited testing No. ATL 0047

PO .Box :2685, Ajman-United Arab Emirates

Tel: 00971-6-7436521, Fax: 00971-6-7439709

Email: uglube@eim.ae , Website: www.unitedgrease.com

Quality Control: F/36; Revision:03; Date: 01/03/2022

For UNITED GREASE AND LUBRICANTS CO. L.L.C



Authorised Signatory